

Technical Data Sheet: Z-CEPDM-140

Closed Cell EPDM Foam — 140kg/m³

Z-CEPDM-140 is a closed-cell EPDM rubber foam that is spongy and compressible foam. It is good for heat, cold and ozone resistant. Suitable to be used in construction works, automotive, insulation, electrical and electronic industries.

Closed Cell EPDM
Foam



Characteristics

- High heat resistance
- High thermal insulation
- High impact elasticity

Applications

- Suitable to be used as an air and watertight seal or insulation including in construction, HVAC, transportation, automotive and general appliances and machinery

Properties

Properties	Z-CEPDM-140	Standard
Colour	Black	—
Size (WxLxT) (mm)	1000x2000x1	ASTM D3574
Density (kg/m ³)	140 ± 20	ASTM D3574
Tensile Strength (kPa)	> 450	ASTM D412
Hardness (shore c)	15 ± 3	JIS K6767
Heat Aging Lineal Shrinkage	< 5	ISO: 2011 Method B

Technical Data Sheet: Z-CEPDM-140

Closed Cell EPDM Foam — 140kg/m³

(70°C, 4h) (%)		
Elongation at Break (%)	> 150	ASTM D412
Tear Strength (KN/M)	> 2.0	ASTM D624
Water absorption (%)	< 5	ASTM D1056
Compression Force at 25% Deflection (kPa)	45 ± 20	ASTM D1056
Compression Set (%)	< 40	ASTM D395

Remark: Technical Data Sheet reflect the average performance of products based on data from controlled standard testing environments and engineering experience but are not guaranteed. User should independently determine the suitability of this material for their specific purpose, assume all risk and liability

